



ORCA WASHED GRAVEL 1/2" x No.4 (12.5 x 4.75mm)

Orca concrete aggregates are produced at the Orca Quarry, Port McNeill, B.C., in a modern and efficient washing and processing plant opened in March 2007 and distributed via ocean-going ships or barges.

The California Department of Transportation has established that aggregates from this source are innocuous with respect to Alkali Silica Reactivity and has approved them for use in reduced mineral admixture concrete.

Caltrans # 22-CAN-2

<u>Caltrans Innocuous List</u> <u>Caltrans Aggregate Prequalification</u>

GRADATION – PERCENTAGE PASSING

Sieve Size		Orca Gravel (Tested Values)	Specifications				
			CALTRANS			ASTM C33-03	
			Per: 90-1.02C (4)(a)(b) 2022			Type 7	
19.0 mm	(3/4")	100		100			
12.5 mm	(1/2")	92		90 - 100			
9.5 mm	(3/8")	61	X = 60	45 - 75	X = ± 15	40 - 70	
4.75 mm	(#4)	9	0 - 15			0 - 15	
2.36 mm	(#8)	2	0 - 6			0 - 5	

TYPICAL PROPERTIES

Testing			Specifications			
Test Name	Orca Value	СТМ	ASTM	Caltrans	ASTM	
Specific Gravity, SSD	2.89		C127			
Absorption	0.5	206	C127			
Dry Rodded Unit Weight, pcf	112	212	C29			
Cleanness Value	94	227		75 Min.		
Durability	90	229				
Soundness	1.0%		C88		12% Max	
Soundness	0.0%	214		10% Max		
Los Angeles Abrasion (500 Revs)	10%	211	C131	45% Max	50% Max	
Materials Finer Than No. 200	0.9%		C117		1% Max	
Lightweight Pieces (Coal or Lignite)	0.0%		C123		0.5% Max	
Lightweight Pieces (Chert & Shale)	0.2%		C123		5% Max	
Clay Lumps, Coarse	0.0%		C142		5% Max	
Alkali Silica Reactivity	Innocuous		C1567		0.10% Max	
Alkali Silica Reactivity	Innocuous		C1293		0.04% Max	
Alkali Silica Reactivity	Innocuous		C1260		0.10% Max	



SPECIAL NOTES

1) This material carries an Environmental Product Declaration

This declaration has been prepared in accordance with ISO 14025, ISO 21930, and ASTM International's EPD program operator rules.

Index List (https://www.astm.org/CERTIFICATION/EpdAndPCRs.html)

Specific EPD

(https://www.astm.org/CERTIFICATION/DOCS/344.EPD Polaris Materials final.pdf)



This product complies with NSF/ANSI 61, 372 and all other applicable requirements

3) All testing has been performed at accredited 3rd party laboratories in accordance with applicable ASTM and CalTrans methods.





Scott Dryden

President & CEO Orca Sand & Gravel LP.